

# PIATRA ONLINE

021 9907 / office@piatraonline.ro

Aleea Teisani nr.137A, sector 1, 014034 Bucuresti

| CARACTERISTICI:<br>L'ALTRA-PIETRA-<br>MODERN |                                                                                     | CARACTERISTICI<br>TEHNICE                                   | STANDARD     | LIMITE STABILITE  |          | L'ALTRA PIETRA®                                        |
|----------------------------------------------|-------------------------------------------------------------------------------------|-------------------------------------------------------------|--------------|-------------------|----------|--------------------------------------------------------|
| REGULARITATE                                 |    | LUNGIME SI LATIME                                           | ISO 10545-2  | ± 0.6 %           | ± 2 mm   | CONFORM                                                |
|                                              |    | GROSIME                                                     | ISO 10545-2  | ± 5.0 %           | ± 0,5 mm | CONFORM                                                |
|                                              |    | RECTANGULARITATE                                            | ISO 10545-2  | ± 0.5 %           | ± 2 mm   | CONFORM                                                |
|                                              |    | RECTITUDINEA LATURILOR                                      | ISO 10545-2  | ± 0.5 %           | ± 1,5 mm | CONFORM                                                |
|                                              |   | PLATITUDINEA SUPRAFEȚEI                                     | ISO 10545-2  | ± 0.5 %           | ± 2 mm   | CONFORM                                                |
| STRUCTURA                                    |  | ABSORBTIE DE<br>APA                                         | ISO 10545-3  | ≤ 0.5 %           |          | CONFORM                                                |
|                                              |  | REZISTENTA LA<br>RUPERE                                     | ISO 10545-4  | ≥ 1300 N          |          | >10000 N                                               |
|                                              |                                                                                     | MODULUL DE RUPERE                                           | ISO 10545-4  | ≥ 35 N/mm²        |          | ≥ 35 N/mm²                                             |
| TERMO-HIGROMETRIC                            |  | EXPANSIUNE TERMICA LINEARA                                  | ISO 10545-8  | VALOARE DECLARATA |          | $\alpha \leq 9 \cdot 10^{-6} \text{ } ^\circ \text{C}$ |
|                                              |  | REZISTENTA LA SOC TERMIC                                    | ISO 10545-9  | TEST VALID        |          | GARANTAT                                               |
|                                              |  | REZISTENTA LA INGHET                                        | ISO 10545-12 | TEST VALID        |          | GARANTAT                                               |
|                                              |  | REACTIA LA FOC                                              | EN 14411     | TEST VALID        |          | A1 FL / A1                                             |
| CHIMIC                                       |  | REZISTENTA LA PRODUSE<br>CHIMICE (ACIDI, BAZE SI<br>SARURI) | ISO 10545-13 | UB MINIM          |          | GARANTAT                                               |

# PIATRA ONLINE

021 9907 / office@piatraonline.ro

Aleea Teisani nr.137A, sector 1, 014034 Bucuresti

|           |                                                                                   |                         |              |                   |            |
|-----------|-----------------------------------------------------------------------------------|-------------------------|--------------|-------------------|------------|
|           |  | REZISTENTA LA PETE      | ISO 10545-14 | $\geq 3$          | 5 GARANTAT |
| SIGURANTA |  | REZISTENTA LA ALUNECARE | DIN 51130    | VALOARE DECLARATA | R11        |
|           |  | REACTIE LA FOC          | EN 13501-1   | CLASA DECLARATA   | A1 FL / A1 |

In conformitate cu standardele EN 14411 (ISO 13006) anexa G grupul